

MONNELI RASANTE P-20S+

High Strength Cementitious Ready Dry Mix Plaster

Product Description

A high strength cement based ready mix plaster. It is specially formulated for exterior and interior plastering work that gives an extra hard, smooth, and better shrinkage control base coat. Due to its exceptional content of additives and the use of precisely graded fillers, a homogeneous, superior adhesion, and a high workability product is obtained when mixed with water.

RASANTE P-20S+ is manufactured to provide a very good quality of plaster and can be applied manually by hand or by using spray machines.

Uses

RASANTE P-20S+ has an extensive use in both residential and commercial complexes in civil engineering and other areas of construction and interior designing due to its optimum compressive strength that could be acquired within a considerably short period of time.

RASANTE P-20S+ is recommended for plastering on block walls, ceilings, columns, bricks and concrete surfaces; it should not be used on painted surfaces.

Advantages

- High compressive and flexural strength
- Very good impact strength
- Easy to mix, apply and finish
- Excellent adhesion to the substrate

Instruction for Use

Surface Preparation

The substrate should be free of loose particles, dust, dirt, grease, oil or paint. Absorbent and porous substrates should be moistened with water prior the application of RASANTE P-20S+.

In case of non absorbent surfaces, a spatter dash slurry coat DASHBOND or DASHBOND SPX (in case of AAC Block surface) should be applied as a key coat to improve adhesion and high bonding with the substrate.

In case of surface contains micro-silica, DASHBOND SPX spatter dash slurry should be applied to improve adhesion with the substrate.

Concrete or block substrates should have been allowed to cure sufficiently. All shrinkage movements should taken place before applying RASANTE P-20S+.

Do not apply RASANTE P-20S+ on surface exposed to movement, vibration or mechanical impacts.

Saturate the surface with water and wait for the evaporation of excess water before applying the mix.

Mixing

RASANTE P-20S+ should be mixed with clean cold water to obtain a homogeneous mixture free from lumps. One 50 Kg. bag of RASANTE P-20S+ should be mixed with about 8 – 9 Liters of clean water. The mixture remains workable for 1 hour after mixing (at +25°C). Let the mix set for 5 minutes, then remix before application.

Application

Apply RASANTE P-20S+ on the surface manually with a plastering trowel or by using a spraying machine in a single layer (up to 20mm). When the plaster has “set”, smooth finishing can be achieved with a wooden or foam float. The Float should be moistened during the smoothing operation.

If more thickness is required, the application should be done in two layers. In the first layer, apply RASANTE P-20S+ in a thickness of 10-15mm, a rough texture is to be obtained to provide mechanical Key for the second layer. The second layer should be applied at least 48 hours after the first layer. Within this period cure the plaster with clean water. Apply the second layer at a thickness of up to 20mm.

If applying with spray machine, RASANTE P-20S+ mix should not be allowed to stand unused in the machine for longer than 30 minutes.

In order to ensure proper curing, it is advisable to keep the plastered surface moist and protected from sun and wind during the first 48 hours.

Cleaning

Tools and equipment should be cleaned with water immediately after use. Hardened materials should be mechanically removed.

Recommendations

- No further water should be added to the mix. Hard and set plaster should not be re-mixed or used
- Do not apply RASANTE P-20S+ onto gypsum, metallic and wooden supports
- During summer season, working area should be covered to prevent the direct sun effects. Keep equipment cool and use a cold water
- The applied plaster has to be water cured for a period of 3 days
- Before applying any kind of stucco finish, paint, or wall paper the plaster has to be allowed to dry out completely
- Should not be applied on floors or on painted surfaces

Applicable Standards

- BS 5262, BS 5492
- ASTM C 387, ASTM C109

Consumption

Approximately 15-16 kg per m² for 10 mm thickness

Packaging

RASANTE P-20S+ is supplied in 50kg multilayered bags

Technical Data

| Properties | Results |
|--|------------------------------|
| Appearance | Grey powder |
| Dry density at 25°C | 1.70 kg/L |
| VOC | 1.2g/L |
| Grain size | 0 – 2.5 mm |
| Pull out strength | > 0.5 N/mm ² |
| Adhesion with DASHBOND SPX | >1.5 N / mm ² |
| Compressive strength at 28 days (ASTM C 579) | Up to 25 N / mm ² |
| Flexural strength at 28 days (ASTM C 580) | > 2.0 N / mm ² |

All values are subject to 5-10 % tolerance

Storage

Store in dry covered place in the original closed bags. In these conditions, the product shelf life is 12 months from the date of production.

Health & Safety

RASANTE P-20S+ is a cement based product. Avoid contact with eyes or skin.

During application, wear appropriate protective clothing, goggles, gloves and respiratory equipment if necessary. In case of contact with skin, rinse with water and again wash thoroughly with soap and water. In case of contact with eyes, rinse with plenty of water and seek medical advice accordingly. If ingested, obtain medical attention immediately. Do not induce vomiting.

The information in this Technical Data Sheet is based on Colmef Monnelli's experience. Colmef Monnelli does not accept any liability arising from the use of its products as it has no direct or continuous control over where or how its products are applied. All Colmef Monnelli's Data Sheets are updated on regular basis. It is the user's responsibility to obtain the latest version.

DUBAI
ABU DHABI
KSA
ITALY

P.O. Box 123808 Dubai UAE
P.O. Box 127326 Abu Dhabi, UAE
P.O. Box 335896 Code: 11383 - Riyadh KSA
Z.I. Ponte d'Assi 06024 Gubbio (PG)

T. +971 4 8803488 F. +971 4 8803450
T. +971 2 5511949 F. +971 2 5511749
T. +966 1 2654277 F. +966 1 2654335
T. +39 75 9221297 F. +39 75 9221174

colmef@colmef.ae

www.colmef-me.com

RASANTE P-20S+
Technical Data Sheet
Edition: January 2020
Revision: 02