

MONNELI ASFABIT RBL

Rubberized Bitumen Emulsion

Product Description

A cold applied rubberized bitumen emulsion in dark brown color that, when dries, it forms tough black seamless and flexible coating.

Uses

ASFABIT RBL can be used as follows:

- Provides a sandwich membrane between screed flooring
- A waterproofing coat for concrete foundations, bricks, retaining walls, etc.
- It can be used to waterproof walls and floors in wet areas
- For maintenance of many types of roofs including built up felt, aluminum, concrete, lightweight screed, timber, slate, asbestos, bitumen sheets, etc.
- As a vapour/salt barrier for exterior walls to building facades behind granite, marble, stone, cladding, curtain walls, etc.
- Can be used as adhesive for insulation boards and expanded polystyrene
- As curing compound for freshly cast concrete

Advantages

- Economical
- Water based with excellent adhesion
- Non-flammable
- Easily applied by brush or squeegee.
- Excellent resistant to alkalis, mild acids, chlorine
- Compatible with all bituminous products
- Resistant to chlorides and sulfates

Instructions for Use

Surface Preparation

The surface of the concrete shall be sound, clean and uncontaminated.

This preparation shall be such as to leave a sound exposed concrete surface free from dust, loose particles and any deleterious matter. If the concrete surface is defective or has laitance, it must be cut back to a sound base.

Moss and lichen must be removed physically followed by treatment with fungicidal wash. After treatment, it must be washed down thoroughly with clean water and allow to dry.

Priming

Hot, very dry or porous surfaces should be primed before applying ASFABIT RBL.

Mixing

ASFABIT RBL should be stirred before use until a uniform color and consistency is achieved. Product is ready for use.

Application

For waterproofing underground structures, the bituminous emulsion shall be applied by brush or roller depending on the dry film thickness required 400 micron dry film thickness (DFT) can be achieved when applied at 1m² /Lt/coat. The two coats must be applied at right angles to one another with a minimum of 6hours intervals between each application on at 35°C. Ensure that coat is completely dry before the next coat is applied.

Cleaning

ASFABIT RBL products should be removed from tools, equipment and mixers with clean water prior to the initial set. Cured material can only be removed mechanically.

Recommendation

- Do not apply subsequent applications if the membrane is punctured or damaged.

Technical Data

Properties	Results
Appearance	Dark brown dries to seamless black coating
Density at 25°C	1.0 kg/L
VOC	30.0 g/L
Solid content	35% ± 2
Rubber content	10% in the dried film
Water resistance	Good
Chloride resistance	Excellent
Flash point	Non-flammable
Application temperature	+5°C to +45°C
Service temperature	−5°C to +80°C

All values are subject to 5-10% tolerance

Applicable Standards

- ASTM D 1187, D 2939
- BS 8102
- ASTM D1227 13 , Type II, Class 2

Consumption

2 to 4 m² / liter

Packaging

ASFABIT RBL is packed in 20 and 200 Liter Drums.

Storage

Should be stored under cover away from extreme heat or direct sunlight or frost. Shelf life is 12 months in tightly sealed containers if stored properly.

Health & Safety

ASFABIT RBL is non-flammable, non-hazardous product. However, proper measures should be taken during work to avoid contact with eyes or skin. In the event of contact with eyes, irrigate immediately with clean water and seek medical care.

The information in this Technical Data Sheet is based on Colmef Monnelli's experience. Colmef Monnelli does not accept any liability arising from the use of its products as it has no direct or continuous control over where or how its products are applied. All Colmef Monnelli's Data Sheets are updated on regular basis. It is the user's responsibility to obtain the latest version.

DUBAI
ABU DHABI
ITALY

P.O. Box 123808 Dubai UAE
P.O. Box 127326 Abu Dhabi, UAE
Z I Ponte d'Assi 06024 Gubbio (PG)

T. +971 4 8803488 F. +971 4 8803450
T. +971 2 5511949 F. +971 2 5511749
T. +39 75 9221297 F. +39 75 9221174

ASFABIT RBL
Technical Data Sheet
Edition: August 2023
Revision: 05

colmef@colmef.ae

www.colmef-me.com