

MONNELI EPOFINISH FC

Fast Cure Solvent-Free Epoxy Repair Mortar for Concrete Floors

Product Description

A solvent free repair mortar for floors based on formulated epoxy resin, curing agents and silica sand specially selected for their ability to be applied and cured in cold temperatures.

Uses

EPOFINISH FC is used in various installations such as:

- Commercial and residential car parking
- Workshops
- Warehousing and storage facilities
- Chemical and pharmaceutical factories
- Food factories and slaughterhouses
- General re-profiling over large areas

Components

- EPOFINISH FC contains Resin (Component A), Hardener (Component B) and graded sand (Component C).
- EPOFINISH FC Resin (Component A) is a low viscosity standard coloured Base which contains fillers and pigments.
- EPOFINISH FC Hardener (Component B) is a low viscosity and low color hardener which, after mixing with the resin can be applied at 100% humidity and on damp floors. The hardener provides excellent chemical and abrasion resistance.
- EPOFINISH FC (Component C) is a graded low dusting silica sand.

Instructions for Use

Surface Preparation

For best finish and adhesion, apply over PRIMER POXY FC.

The concrete must be at least 21 days old. The concrete must be free from loose matter, oil and dirt before starting surface preparation.

The EPOFINISH FC is also designed for deep and wide cracks. The cracks should be opened up by sandblasting or mechanical wire brushing. Undercut if necessary.

Application

Items needed

- Multi-speed drill fitted with a mixing paddle
- Hand held steel trowel
- Clean bucket, steel trowel and SOLVENTE 10 to clean the equipment

Method

Using a drill and a paddle at low speed, stir the resin (Component A) for 1 minute.

Slowly add the Hardener (Component B) and increase mixing speed. Mix for 1 minute, ensuring proper mixing between the base and the hardener.

Slowly add the sand (Component C) and increase mixing speed. Mix for 2 minutes. Do not dump all the sand at once.

Pour the mix onto the floor immediately and spread using a steel trowel. Wet the blade with solvent to aid application.

Technical Data

Properties	Results
Solid content	100%
Kit size	4 Liter
Theoretical coverage	4 m ² / 4 liter
Pot Life at 7°C	80 minutes
Pot Life at 20°C	25 minutes
Thin layer (3mm) Dry time at 7°C	15 hours
Thin layer (3mm) Dry time at 25°C	2.5 hours
Mixing ratio HARDENER: BASE: SAND (by weight)	0.36 : 1.00 : 6.65
Mixed density at 20°C	2.00 kg/L
Application maximum relative humidity	100%
Compressive strength (ASTM C579)	> 80.0 N / mm ²
Bending strength (ASTM C580)	> 20.0 N / mm ²
Tensile strength (ASTM C307)	> 12.0 N / mm ²
Bond strength to concrete (ASTM D4541)	> 2.0 N / mm ²
Taber abrasion (ASTM D4060 CS17 Wheels)	60 mg loss/1000 cycles
Water absorption (ASTM D413) (maximum)	0.001%
Porosity with no sealer NACE Sand TM-01-74	0
Hardness shore D	85

All values are subject to 5-10 % tolerance

Cleaning

Clean equipment with SOLVENTE 10. In case of spillage, use fine silica or cement to absorb the spill and dispose of according to local regulations.

Packaging

EPOFINISH FC is supplied as a pre-measured kit depending on the customer's requirements. Our standard packaging is 4 liter kit.

Storage

Keep in tightly closed containers and in sheltered and dry place with a temperature between 5°C and 35°C. In these conditions it maintains its characteristics unchanged for 12 months.

Health & Safety

Study the MSDS of the product before use or storage.

EPOFINISH FC is not regulated per the "Directive 67/548/EEC EU Dangerous Materials List" so no special labeling is needed.

The information in this Technical Data Sheet is based on Colmef Monnelli's experience. Colmef Monnelli does not accept any liability arising from the use of its products as it has no direct or continuous control over where or how its products are applied. All Colmef Monnelli's Data Sheets are updated on regular basis. It is the user's responsibility to obtain the latest version.

DUBAI
ABU DHABI
KSA
ITALY

P.O. Box 123808 Dubai UAE
P.O. Box 127326 Abu Dhabi, UAE
P.O. Box 335896 Code: 11383 - Riyadh KSA
Z.I. Ponte d'Assi 06024 Gubbio (PG)

T. +971 4 8803488 F. +971 4 8803450
T. +971 2 5511949 F. +971 2 5511749
T. +966 1 2654277 F. +966 1 2654335
T. +39 75 9221297 F. +39 75 9221174

EPOFINISH FC
Technical Data Sheet
Edition: January 2020
Revision: 02

colmef@colmef.ae

www.colmef-me.com