

MONNELI EPOFLOOR E250 (IF)

Solvent-Free Epoxy Topcoat for Concrete Floors

Product Description

A solvent free coating based on formulated epoxy resin and curing agents specially selected for their ability to be applied and cured in warm temperatures.

Uses

EPOFLOOR E250 (IF) has a high gloss finish and is used in various installations such as:

- Commercial and residential car parking
- Workshops
- Warehousing and storage facilities
- Chemical and pharmaceutical factories
- Food factories and slaughterhouses
- Schools and office buildings

Components

- EPOFLOORE 250 (IF) contains resin (Component A) and hardener (Component B):
- EPOFLOORE 250 (IF) resin (Component A) is a low viscosity standard coloured base which contains fillers and pigments.
- EPOFLOORE 250 (IF) hardener (Component B) is a low viscosity and low color hardener which, after mixing with the resin, is less-yellowing and can be applied at 75% humidity. The hardener (Component B) provides excellent chemical and abrasion resistance.

Instructions for Use

Surface Preparation

The concrete must be at least 28 days old. The concrete must be free from loose matter, oil and dirt before starting surface preparation.

The best method to prepare the surface is dry grinding using a specialized planetary grinder. Before grinding, the surface must be free from any degreasing or cleaning chemicals which may have been used. At the end of grinding, the surface should be flat.

Surface irregularities and blow holes shall be repaired with EPOFINISH IF. When the filler is hardened, grinding and leveling of the patched area is recommended to ensure a good finish.

Ensure dust is removed from the surface using an industrial vacuum.

For best finish and adhesion, treat the surface with PRIMER POXY (IF). In case the surface is very absorbent, apply a second coat of primer within the allowed recoating time.

Application thickness

- A thickness of 200-500µm per coat over a primer is recommended
- For anti-slip finish, broadcast Silica Sand with the required size onto the first coat while wet, once cured, remove excess sand and apply the final coat

Application

Items Needed

- Multi-speed drill fitted with a mixing paddle
- Good quality medium haired non-shedding roller, suitable for epoxy application. Ensure that all loose hair on the roller have been removed before use.
- 7" flat trowel
- Clean bucket, 2" brush and SOLVENTE 10 to clean the equipment

Method

Using a drill and a paddle at low speed, stir the resin (Component A) for 1 minute.

Slowly add the hardener (Component B) and increase mixing speed. Mix for 3-4 minutes, ensuring proper mixing between the resin and the hardener components, until a completely homogeneous streak free mix of uniform color is obtained.

The best method to apply the mixed product is by pouring it over the prepared surface. Then using a flat trowel, spread the material uniformly over the surface and back roll it maintaining the recommended thickness. Using just the roller is also possible.

Cleaning

Clean equipment with SOLVENTE 10. In case of spillage, use fine silica or cement to absorb the spill and dispose of according to local regulations.

Packaging

EPOFLOOR E 250 (IF) is supplied as a pre-measured kit depending on the customers' requirements. Our standard packaging is 4 Liter and 15 Liter kit.

Storage

Keep in tightly closed containers and in sheltered and dry place with a temperature between +5°C and +35°C. In these conditions, it maintains its characteristics unchanged for 12 months.

Health & Safety

Study the MSDS of the product before use or storage.

EPOFLOOR E 250 (IF) is not regulated per the "Directive 67/548/EEC EU Dangerous Materials List" so no special labeling is needed

Technical Data

Properties	Results
Solid content	100%
Recommended DFT / coat	200-500 microns
Kit size	4 Liter
Theoretical coverage	8-20 m ² / 4 liter kit
Kit size	15 Liters
Theoretical coverage	30-75 m ² / 15 liter kit
Pot life at 18°C	50 minutes
Pot life at 30°C	30 minutes
Thin film (125µm) Dry time at 25°C	5-6 hours
Mixing ratio HARDENER: BASE (by weight)	1.00 : 3.6
Mixed density at 20°C	1.38 kg/L
Max recoat/topcoat time at 25°C	24 hours
Application maximum relative humidity	75 %
Compressive strength (ASTM C579)	> 80 N / mm ²
Bending strength (ASTM C580)	> 30 N / mm ²
Tensile strength (ASTM C307)	> 15 N / mm ²
Bond strength to concrete (ASTM D4541)	> 2.0 N / mm ²
Taber abrasion (ASTM D4060 CS17 Wheels)	45 mg loss/1000 cycles
Water absorption (ASTM D413) (maximum)	0.001%
Porosity with no sealer NACE Sand TM-01-74	0
Hardness shore D	85

All values are subject to 5-10 % tolerance

The information in this Technical Data Sheet is based on Colmef Monnelli's experience. Colmef Monnelli does not accept any liability arising from the use of its products as it has no direct or continuous control over where or how its products are applied. All Colmef Monnelli's Data Sheets are updated on regular basis. It is the user's responsibility to obtain the latest version.

DUBAI
ABU DHABI
KSA
ITALY

P.O. Box 123808 Dubai UAE
P.O. Box 127326 Abu Dhabi, UAE
P.O. Box 335896 Code: 11383 - Riyadh KSA
Z.I. Ponte d'Assi 06024 Gubbio (PG)

T. +971 4 8803488 F. +971 4 8803450
T. +971 2 5511949 F. +971 2 5511749
T. +966 1 2654277 F. +966 1 2654335
T. +39 75 9221297 F. +39 75 9221174

EPOFLOOR E250 (IF)
Technical Data Sheet
Edition: January 2020
Revision: 02

colmef@colmef.ae

www.colmef-me.com