

MONNELI NEOFIL F8

High Performance Thin Set Waterproof Polymer Modified Tile Adhesive

Product Description

A polymer modified cementitious tile adhesive. It is supplied as grey or white coloured powder. It is water/ weather resistant and does not contain asbestos nor any other harmful components.

Uses

NEOFIL F8 is used for fixing of tiles in interior and exterior applications especially to those exposed to permanently wet condition.

- Institutional kitchen
- Bathrooms
- Shower rooms
- Swimming pools
- Laboratories
- Hospitals
- Ceramic, porcelain tiles, vitrified tiles, granite & marble floors

Advantages

- Enhanced bond and tensile strengths
- Water and Weather resistant
- Eco-friendly
- Non-sagging
- Good open time and slip resistance
- Formulated to suit Middle East conditions

Instruction for Use

Surface Preparation

All surfaces should be sound, clean & uncontaminated. This preparation should leave an exposed concrete surface free from dust, loose particles, deleterious matter, oil, grease, chemical films & other contaminant.

All loose particles of mortar, paint, etc. must be physically removed.

Concrete or blockwork: should be allowed to cure sufficiently so that all shrinkage movements take place before fixing tiles.

Gypsum supports: must be treated with PRIMER A16. Should not have a percentage of humidity more than 10%.

The surface of substrates must be moistened slightly with clean water to reduce the absorption of water from the mortar. Do not moistened the tiles.

Mixing

Place 5.0 – 5.5 liters of cold, potable water (or ELASTOKOL as needed) in the mixing bucket and add slowly 25 kg bag of NEOFIL F8 under continuous mixing till a uniform lump free consistency mix is achieved. For mixing process, a slow speed drill (200- 300rpm) fitted with a suitable paddle is recommended.

Allow the obtained mix to stand for 3 minutes and then remix before application.

Application

Spread NEOFIL F8 on the substrate to a uniform thickness using a toothed spatula, the first pass with its straight edge and the second pass immediately after, to the desired thickness using the toothed part.

Place the tiles onto the adhesive bed. Apply sufficient pressure on the tile during fixing it with slight twisting movement in order to ensure good contact with the adhesive.

In case of large size tiles, it is necessary to spread the adhesive also to the backside of the tile and then place the tiles into the adhesive bed.

Apply enough material that can be tiled during the adhesive's open wet time.

Spreading large areas may result in drying the adhesive before tiles can be fixed causing poor adhesion.

Finishing

Remove excess adhesive with damp cloth before the material has set. Joint grouting between tiles may be commenced 10 hours after tiles have been laid on the walls and 24 hours after tiles are laid on the floors.

Cleaning

Tools and equipment should be cleaned with water immediately after use. Hardened materials should be mechanically removed.

Recommendations

- To achieve improve adhesion strength, it is recommended to replace water with ELASTOKOL
- The grey type presents higher mechanical resistances. It is therefore advisable to use to fix tiles on floor
- Stiffened mortar must neither be diluted with water nor with fresh mortar
- Do not use NEOFIL F8 on metal or non-absorbing surfaces
- Do not apply NEOFIL F8 in rainy weather, high winds and sand storms
- Do not apply under direct sun
- Keep equipment cool and use cold water
- Porosity of tiles and substrates has significant effect on adhesive strength of tiles

Applicable Standards

- EN 12004-C2TE
- ISO 13007 – C2TE
- ANSI A 118.4
- EN 1346
- EN 1348
- ISO 13007/EN 12004: C2TE (S1 when mixed with ELASTOKOL)

Technical Data

Properties	Results
Appearance	Powder
Color	Grey or white
Dry density	1.55 kg/L
Wet density	1.70 kg/L
VOC	<1.0 g/L
Water resistance	Excellent
Slip resistance	Excellent
Open time	Approx. 30 minutes
Workable time	45 minutes
Wall grouting	After 10 hours
Floor grouting	After 24 hours
Shear strength	1.6 N/mm ²
Adhesion strength (EN 1348)	
Initial adhesion at 28 days	1.5 N/mm ²
Adhesion after heat-ageing	1.0 N/mm ²
Adhesion after water immersion	1.1 N/mm ²
Adhesion after Freeze thaw cycle	1.10 N/mm ²

All values are subject to 5-10 % tolerance

Consumption

Approx. 2.5 to 4.5kg NEOFIL F8 per m² using notched trowel on smooth surface. Consumption will vary according to type of tiles and support condition.

Packaging

NEOFIL F8 is packed in 25 kg bags.

Storage

Store in dry covered place in the original closed bags and shelf life is 12 months if stored as recommended.

Health & Safety

NEOFIL F8 can be harmful to skin as it contains cement powders which may release alkalis when mixed with water.

During application, wear appropriate protective clothing, goggles, gloves and respiratory equipment if necessary.

In case of contact with skin, rinse with water and again wash thoroughly with soap and water. In case of contact with eyes, rinse with plenty of water and seek medical advice accordingly.

If ingested, obtain medical attention immediately. Do not induce vomiting.

The information in this Technical Data Sheet is based on Colmef Monnelli's experience. Colmef Monnelli does not accept any liability arising from the use of its products as it has no direct or continuous control over where or how its products are applied. All Colmef Monnelli's Data Sheets are updated on regular basis. It is the user's responsibility to obtain the latest version.

DUBAI
ABU DHABI
KSA
ITALY

P.O. Box 123808 Dubai UAE
P.O. Box 127326 Abu Dhabi, UAE
P.O. Box 335896 Code: 11383 - Riyadh KSA
Z.I. Ponte d'Ássi 06024 Gubbio (PG)

T. +971 4 8803488 F. +971 4 8803450
T. +971 2 5511949 F. +971 2 5511749
T. +966 1 2654277 F. +966 1 2654335
T. +39 75 9221297 F. +39 75 9221174

NEOFIL F8
Technical Data Sheet
Edition: September 2021
Revision: 03