

MONNELI BITUFLEX PLUS

Elastomeric SBS Modified Liquid Applied Waterproofing

Product Description

An SBS modified bituminous liquid membrane composed of elastomers, bitumen, resins and additives. It is a thixotropic paste easily applicable horizontally and vertically. Once dried it forms an elastic, continuous, waterproofing membrane resistant against thermal changes, UV rays and acid rains.

Uses

BITUFLEX PLUS adheres perfectly to several supports as bituminous sheaths, concrete, asbestos, plaster, wood, metallic surfaces, etc.

It is used for waterproofing of variety of supports such as :

- Eaves
- Underground foundations
- Restoration of old bituminous waterproofing
- Chimneys sealing
- Water proofing of shower stalls before the ceramic tiles laying, corrosion protection, etc.
- Waterproofing for wet areas including kitchen, bathroom, balconies & etc.

Its particular composition makes it suitable for applications on humid supports and during winter.

Advantages

- Can be applied vertically and horizontally
- Outstanding waterproof properties to ensure great protection against corrosion
- Easy to use, single component
- Elastomeric
- High elasticity with permanent flexible membrane
- Excellent water resistance after complete hardening

- Excellent adhesion to most building substrates
- Excellent resistance against Chloride and Sulphate ions
- Resistant to underground soil ground water aggressive effect
- Membrane can be easily repaired by spot application

Instructions for Use

Surface Preparation

The surface of the concrete shall be sound, clean and uncontaminated.

This preparation shall be such as to leave a sound exposed concrete surface free from dust, loose particles and any deleterious matter. If the concrete surface is defective or has laitance, it must be cut back to a sound base.

Oil, grease, varnishes, rust, dust and mould on metal surfaces shall be removed by wire or stiff brushing and grit blasting then wiped with SOLVENTE prior to priming.

Moss and lichen must be removed physically followed by treatment with fungicidal wash. After treatment, it must be washed down thoroughly with clean water and allow to dry.

Priming

Highly porous concrete or concrete containing microsilica will require priming with a coat of thin coat of BITUFLEX PLUS. The primer shall be applied at a rate of 5-6 m²/L and left to achieve a tack-free condition to dry before applying the topcoat. A second coat of primer may be required if the substrate is excessively porous.

Application

Two coats of BITUFLEX PLUS shall be applied by brush or squeegee at a rate of 0.6 m²/liter giving a total dry film thickness of 2.0mm thick membrane. For large structural areas, variable mechanical loads, and moving cracks, fibre mesh shall be fixed between the coats.

The two coats must be applied at right angles to one another with a minimum of 6 hour intervals between each application at 25°C. Each coat must be completely dry before the next coat is applied.

A third coat can be applied blinded with clean sand as a protection against foot traffic and/or to provide a good key for top screed.

Do not apply subsequent applications if the membrane is punctured or damaged.

In areas where BITUFLEX PLUS is to receive a render or plaster finish, a keyed surface should be formed by gritting the second coat with clean dry sharp sand as soon as it's applied. The excess sand should not be brushed off when the coating has dried. Allow a minimum period of 48 hours before plastering, rendering or applying floor screed.

Cleaning

BITUFLEX PLUS should be removed from tools, equipment and mixers with clean water prior to the initial set. However, once it has dried, it can only be removed with SOLVENTE 10.

Recommendations

- Do not apply the product a temperature less than +3°C and with humidity more than 90%.
- Do not apply subsequent applications if the membrane is punctured or damaged.
- Protect BITUFLEX PLUS from rain or from traffic till it completely cures. Damaged areas of BITUFLEX PLUS can be repaired by over coating the damaged area. As protective finishing coat it is possible to apply ELASTOGUM or MANTOFLEX.

Technical Data

Properties	Results
Appearance	Black dense liquid
Density at 25°C	1.1 kg / L
Solid content	60% ± 2%
Viscosity	2400 cps
Rubber content	10%
VOC	176.0 g/L
Temperature of application	+5°C to +35°C
Superficial film formation at +25°C	1 hour
Elongation	1000%
Complete hardening	2 days (2 mm thickness)
Tensile resistance (ASTM D412)	0.4 N / mm ²
pH value	10
Recovery for 300% elongation (ASTM D412)	100%
Curing time (25°C)	24 hours
Shore A hardness	30
Vapour permeability	0.18 gr. m ² / 24 hour
Service temperature	-10°C to +80°C
Aging resistance	Excellent
Water resistance after complete hardening	Excellent
Crack bridging	Up to 2 mm

All values are subject to 5-10 % tolerance

Applicable Standards

- ASTM C 309 – 96
- BS 6949:1991
- ASTM D1227

Consumption

1.6 L/m² per 1 mm DFT

Packaging

BITUFLEX PLUS is supplied in metallic containers of 20 liter and 200 liter drums.

Storage

Keep in covered area away from direct sunlight and in tightly sealed containers. In these conditions BITUFLEX PLUS maintains its characteristics for 12 months.

Health & Safety

BITUFLEX PLUS is a solvent based flammable product. Keep away from fire sources during application. Protect eyes during application by using goggles. Splashes to eyes should be washed immediately with abundant water and seek medical treatment.

The information in this Technical Data Sheet is based on Colmef Monnelli's experience. Colmef Monnelli does not accept any liability arising from the use of its products as it has no direct or continuous control over where or how its products are applied. All Colmef Monnelli's Data Sheets are updated on regular basis. It is the user's responsibility to obtain the latest version.

DUBAI
ABU DHABI
ITALY

P.O. Box 123808 Dubai UAE
P.O. Box 127326 Abu Dhabi, UAE
Z.I. Ponte d'Assi 06024 Gubbio (PG)

T. +971 4 8803488 F. +971 4 8803450
T. +971 2 5511949 F. +971 2 5511749
T. +39 75 9221297 F. +39 75 9221174

colmef@colmef.ae

www.colmef-me.com

BITUFLEX PLUS
Technical Data Sheet
Edition: December 2023
Revision: 06