

MONNELI NEOFIL COLOR 0-4

Latex Modified Cementitious Tile Grout for Joints 0-4 mm Wide

Product Description

A fine colored latex modified powder composed of cement, quartz, synthetic resins and waterproofing additives which when mixed with water, gives a smooth, easily applied grouting mortar with high mechanical resistance and compensated shrinkage.

NEOFIL COLOR 0-4 is produced in a variety range of colors which match all types of tiles.

Uses

NEOFIL COLOR 0-4 can be used for sealing up to 4 mm joint width ceramic tiles, clinker, quarry tile, mosaics, etc. It is suitable for floors and walls joints internally and externally, including kitchens and bathrooms.

To obtain high resistant characteristics (heavy traffic) or high waterproofing resistance (swimming pools), it is recommended to mix NEOFIL COLOR 0-4 with GIUNTOLASTIC instead of water.

Advantages

- Ideal for internal and external floors and walls joints.
- Crack free, non-shrinkage grout with high abrasion, compression and flexural strength
- Wide range of color selection
- Suitable for joints width from 0 to 4 mm
- Water and Weather resistant
- Formulated to suit Middle East conditions
- Very Low VOC, Asbestos Free

Instructions for Use

Surface Preparation

Make sure that the tile adhesive is totally set before applying NEOFIL COLOR 0-4 grout. The joints must be clean, free of dust. Clean the joints between tiles and brush before grouting.

Mixing

Measure 3.0 – 3.5 Liters of cold, potable water (or GIUNTOLASTIC instead of water as needed) in the mixing bucket and add slowly 10 kg bag of NEOFIL COLOR 0-4mm under continuous mixing till a uniform lump free consistency mix is achieved.

Application

After mixing, let the material rest for about 10 minutes, then remix and spread using a rubber grout float.

Let the product set for about 20 minutes and then clean with a damp sponge. After the complete hardening, clean all the surface of the tile with a dry cloth.

Cleaning

Remove excess adhesive with a damp cloth before it dries. Joints grouting between tiles may be commenced after 10 hours of tiling for walls and 24 hours for floors.

Recommendations

- Do not apply NEOFIL COLOR 0-4 in rainy weather, high winds and sand storms
- Do not apply on surface that has temperature less than 5°C
- During summer season, working area should be covered to prevent the direct sun effects. Keep equipment cool and use a cool water
- The product should not be exposed to moving water during application
- Apply NEOFIL COLOR 0-4 when the joint is totally dry
- In case of very high absorbent tiles or high temperature, dampen the joints with clean water.

- It is recommended to grout the joints after 24 hours of tile fixing. Since temperature and humidity conditions affect the final curing, it is advisable to allow extended periods of cure when temperatures are low and/ or relative humidity is below 70%.

Technical Data

Properties	Results
Density (dry) at 25°C	1.9 kg/L
VOC	< 5 g/L
Workable time at 25°C	45 minutes
Compressive strength	> 20 N / mm ²
Flexural strength	>3.5 N / mm ²
Adhesion strength	>1.5 N / mm ²
Linear shrinkage	< 2.5 mm/m
Tensile strength	2.5 N / mm ²
Water absorption	< 10g
Noxiousity CEE 88/379	No

All values are subject to 5-10 % tolerance

Applicable Standards

- European EN 13888 – CG1
- ANSI A 118.7
- ISO 13007-3 as CG1

Packaging

NEOFIL COLOR 0-4 is supplied in 10 and 20 Kg bags.

Storage

Store in a dry covered place in original well closed packaging. Shelf life is 12 months if stored as recommended.

Health & Safety

NEOFIL COLOR 0-4 can be harmful to skin as it contains cement powders which may releases alkalis when mixed with water.

During application, wear appropriate protective clothing, goggles, gloves and respiratory equipment if necessary.

In case of contact with skin, rinse with water and again wash thoroughly with soap and water.

In case of contact with eyes, rinse with plenty of water and seek medical advice accordingly.

If ingested, obtain medical attention immediately. Do not induce vomiting

Consumption

Size of the Tile (mm)	Width of the Joint (mm)				
	2	3	5	8	10
100 X 100 X 6	0.4	0.6	1.0		
150 X 150 X 6		0.4	0.6		
200 X 200 X 8		0.4	0.6		
250 X 250 X 8		0.3	0.8	1.2	1.5
300 X 300 X 9		0.3	0.4	0.7	0.9
300 X 300 X 10		0.3	0.5	0.9	1.1
300 X 600 X 10		0.2	0.4	0.6	0.9
400 X 400 X 10		0.2	0.4	0.6	0.8
600 X 600 X 12			0.4	0.5	0.6

For different size of tiles or width of joints, the consumption can be calculated using either of the two following formulas:

Formula 1:

$$\frac{W \times D}{1,000} \times L \times 1.9 = \text{Kg. /m}^2$$

W = width of joint (mm)
D = thickness of tile (mm)
L = linear meter of joints in 1 m² of tiles
A = length of tile (mm)
B = width of tile (mm)

Formula 2:

$$\frac{A + B}{A \times B} \times W \times D \times 1.9 = \text{Kg. /m}^2$$

The information in this Technical Data Sheet is based on Colmef Monnelli's experience. Colmef Monnelli does not accept any liability arising from the use of its products as it has no direct or continuous control over where or how its products are applied. All Colmef Monnelli's Data Sheets are updated on regular basis. It is the user's responsibility to obtain the latest version.

DUBAI
ABU DHABI
ITALY

P.O. Box 123808 Dubai UAE
P.O. Box 127326 Abu Dhabi, UAE
Z.I. Ponte d'Assi 06024 Gubbio (PG)

T. +971 4 8803488 F. +971 4 8803450
T. +971 2 5511949 F. +971 2 5511749
T. +39 75 9221297 F. +39 75 9221174

NEOFIL COLOR 0-4
Technical Data Sheet
Edition: December 2021
Revision: 03

colmef@colmef.ae | www.colmef-me.com