

# MONNELI NEOFIL TILE GLUE PLUS

*Water Resistant Ceramic Tile Adhesive*

## Product Description

---

A premixed cement based ceramic tile adhesive. It is water resistant, and it does not contain asbestos nor any other harmful components.

## Uses

---

NEOFIL TILE GLUE PLUS is used for permanent fixing of ceramic tiles for internal & external applications. It is suitable for use in:

- Kitchens
- Bathrooms
- Regular Rooms

## Advantages

---

- Water resistant
- Economical
- Eco-friendly
- Formulated to suit Middle East conditions

## Instructions for Use

---

### Surface Preparation

All surfaces should be sound, clean & uncontaminated. This preparation should leave an exposed concrete surface free from dust, loose particles, deleterious matter, oil, grease, chemical films & other contaminant.

All loose particles of mortar, paint, etc. must be physically removed.

Concrete or blockwork: allowed to cure sufficiently so that all shrinkage movements take place before fixing tiles.

Gypsum supports: treat with PRIMER A16. Should not have a percentage of humidity more than 10%.

The surface of substrates must be moistened slightly with clean water to reduce the absorption of water from the mortar. Do not moisten the tiles.

### Mixing

Place 4.5–4.8 liters of cold, potable water (or ELASTOKOL as needed) in the mixing bucket and add slowly 25 kg bag of NEOFIL TILE GLUE PLUS under continuous mixing till a uniform lump free consistency mix is achieved. For mixing process, a slow speed drill (200- 300rpm) fitted with a suitable paddle is recommended.

Allow the obtained mix to stand for about 5 minutes and then remix before application..

### Application

Spread NEOFIL TILE GLUE PLUS on the substrate to a uniform thickness using a toothed spatula, the first pass with its straight edge and the second pass immediately after, to the desired thickness of NEOFIL TILE GLUE PLUS using the toothed part. Place the tiles onto the adhesive bed. Apply sufficient pressure on the tile during fixing it with slight twisting movement in order to ensure good contact with the adhesive.

In case of large size tiles, it is necessary to spread the adhesive also to the backside of the tile and then place the tiles into the adhesive bed.

Apply enough material that can be tiled during the adhesive's open wet time. Spreading large areas may result in drying the adhesive before tiles can be fixed causing poor adhesion.

### Finishing

Remove excess adhesive with a damp cloth before it dries. Joints grouting between tiles may be commenced after 10 hours of tiling for walls and 24 hours for floors.

### Cleaning

Tools and equipment should be cleaned with water immediately after use. Hardened materials should be mechanically removed.

## Recommendations

- To achieve improve adhesion strength, it is recommended to replace water with ELASTOKOL.
- Stiffened mortar must neither be diluted with water nor with fresh mortar
- Do not use NEOFIL TILE GLUE PLUS on metal or non-absorbing surfaces.
- Do not apply NEOFIL TILE GLUE PLUS in rainy weather, high winds and sand storms
- Do not apply under direct sun
- Keep equipment cool and use cold water
- Porosity of tiles and substrates has significant effect on adhesive strength of tile

## Applicable Standards

- ISO 13007/EN 12004: C1T
- EN 1346/EN 1348
- ANSI A 118.1, ANSI A 118.4 (with Elastokol)

## Consumption

Approx. 2.5 to 4.5kg NEOFIL TILE GLUE PLUS per m<sup>2</sup> using notched trowel on smooth surface. Consumption will vary according to type of tiles and support condition.

## Packaging

NEOFIL TILE GLUE PLUS is packed in 25 bags.

## Storage

Store in dry covered place in the original closed bags and shelf life is 12 months if stored as recommended.

## Technical Data

Properties	Results
Appearance	Grey or White Powder
Density	Dry: 1.55 kg/L Wet: 1.70 kg/L.
VOC	< 1.0 g/L
Open time	Approx. 10 minutes
Workable time	45 minutes
Wall grouting	After 10 hours
Floor grouting	After 24 hours
Ready to use	After 14 days
Shear strength	> 0.65 N/mm <sup>2</sup>
Adhesion strength (EN 1348)	
Initial adhesion at 28 days	1.0 N/mm <sup>2</sup>
Adhesion after heat ageing	0.7 N/mm <sup>2</sup>
Adhesion after water immersion	0.7 N/mm <sup>2</sup>
Adhesion of the freeze thaw	0.8 N/mm <sup>2</sup>

All values are under standard lab conditions

## Health & Safety

NEOFIL TILE GLUE PLUS can be harmful to skin as it contains cement powders which may releases alkalis when mixed with water.

During application, wear appropriate protective clothing, goggles, gloves and respiratory equipment if necessary.

In case of contact with skin, rinse with water and again wash thoroughly with soap and water. In case of contact with eyes, rinse with plenty of water and seek medical advice accordingly. If ingested, obtain medical attention immediately. Do not induce vomiting.

The information in this Technical Data Sheet is based on Colmef Monneli's experience. Colmef Monneli does not accept any liability arising from the use of its products as it has no direct or continuous control over where or how its products are applied. All Colmef Monneli's Data Sheets are updated on regular basis. It is the user's responsibility to obtain the latest version.

DUBAI  
ABU DHABI  
KSA  
ITALY

P.O. Box 123808 Dubai UAE  
P.O. Box 127326 Abu Dhabi, UAE  
P.O. Box 335896 Code: 11383 - Riyadh KSA  
Z.I. Ponte d'Assi 06024 Gubbio (PG)

T. +971 4 8803488 F. +971 4 8803450  
T. +971 2 5511949 F. +971 2 5511749  
T. +966 1 2654277 F. +966 1 2654335  
T. +39 75 9221297 F. +39 75 9221174

**NEOFIL TILE GLUE PLUS**  
Technical Data Sheet  
Edition: April 2021  
Revision: 00