

INDUSTRIAL FLOORING

MONNELI NEOCEM SCREED LC

Pre-mixed Floor Screed

Product Description

A ready to use cement based floor screed. It is a single compound formulated specially from hydraulic cement, graded aggregates and fibers. It is ideal for leveling and smoothing uneven floors prior to laying decorative floor coverings, carpets, floor tiles, or any other finishing.

Uses

NEOCEM SCREED LC can be applied on any type of support as long as it is not subjected to rising humidity, like old or new concrete and stone. It is used to level horizontal surfaces prior to laying floor coverings.

NEOCEM SCREED LC is used to produce bonded, unbonded and floating screeds in internal areas. It is not recommended on ground supported concrete slabs without damp proof membrane.

Advantages

- Good workability properties, good compaction
- Eco-friendly Low VOC

Instructions for Use

Surface Preparation

The surface should be sound, clean free from loose material, grease, laitance, dirt curing compound, etc.

Bonded screed (thickness from 10 to 50mm)

Shrinkages The base concrete should be sound, clean and uncontaminated. The surface must be well prepared for bonding by scabbing to expose the coarse aggregate. Fix any screed battens to level.

The surface should be swept to remove any loose material and wetted with clean water if the screed is placed in direct contact with the base.

Priming

NEOCEM SCREED LC can be laid as a bonded screed by applying SBR Bonding Slurry to prepared concrete substrate as a bonding and priming layer. To prepare the SBR bonding slurry, mix 1 part of SBR LATEX RIPRESA with 2 parts of clean water and add 3 parts by weight of fresh cement and mix until a smooth consistency is achieved.

Scrub the mixed slurry into the concrete surface, while the slurry is not yet dry; apply NEOCEM SCREED LC in order to ensure good adhesion with the substrate.

Un-bonded screed (minimum thickness 50mm)

Concrete substrates should be neutralized by soaking with clean water prior to screed application. Free water on the surface should be allowed to disperse before laying the screed.

Floating Screed (minimum thickness 50mm)

For floating screed, place a suitable separating or damp proof membrane over the substrate before applying the screed mortar.

<u>Mixing</u>

Pour into a container 4-6 liters of water for 50 kg bag of NEOCEM SCREED LC. Add the powder screed to the water and mix with a low speed electric drill fitted with a suitable paddle, until a uniform, lump free consistency mix is achieved. No further water should be added to the mix. Do not add water to the mix once it starts to set.

Application

Pour the mixed product onto the surface and spread to the level at the recommended thickness above the bottom i.e.: giving it a surcharge. Then tamp down the screed heavily to the level to give it full compaction. Strike off excess screed material until the top level (above the batten) by running a straight edge ruler alongside it.

Fill any slightly low areas, re-compact and rule out. Finish the section of the screed just laid by wood float and steel trowel.

Protect the floor after leveling the mix from direct sunlight, high winds or rain.

It is possible to apply flooring material on top of NEOCEM SCREED LC (such as ceramic, carpet, etc.) after nearly 7 days (depending on the thickness, the supports humidity and the weather conditions).

Curing

Curing of the completed floor shall be carried out using a combination of damp hessian and polythene sheeting for a period of no less than 3 days.

Cleaning

Tools and equipment should be cleaned with water immediately after use. Hardened materials should be removed mechanically.

Recommendations

- During summer season or temperature higher than 35°C, working area should be covered to prevent the direct sun effects. Keep equipment cool and use cool water.
- Protect the freshly applied NEOCEM SCREED LC from direct sunlight and/or strong drying wind.
- NEOCEM SCREED LC should be cured for minimum 3 days with clean water.
- Most floor covering can be laid after 7 days.
- When applying the screed over tongue and groove timber floors or other surfaces, it is recommended to reinforced the screed with expanded metal or galvanized wire mesh.
- Do not use where negative hydrostatic pressure is evident (i.e. rising damp).

Consumption

2.0 kg/m² per millimeter of thickness

Storage

Keep in sheltered and dry place with a temperature between +5°C and +35°C. Shelf life is 12 months from date of production if stored properly.

Technical Data

Properties	Results
Appearance	Powder
Color	Grey
Wet density at 25°C	2.1 kg/L
Workable time at 25°C	>20 mins
VOC	0.2 g/L
Aggregate size	0-4mm
Compressive strength at 28 days (BS EN 196-1)	30 N / mm²
Flexural strength at 28 days (BS EN 196-1)	>5 N / mm²
Tensile adhesion strength (BS 1881)	>1.5 N/mm²
Open to foot traffic at 25°C	48 hours
Full traffic use at 25°C	28 days
Service temperature	-5°C to +80°C

All values are subject to 5-10 % tolerance

Packaging

NEOCEM SCREED LC is supplied 50 Kg bags.

Health & Safety

During application, wear appropriate protective clothing, goggles, gloves and respiratory equipment if necessary.

In case of contact with skin, rinse with water and again wash thoroughly with soap and water. In case of contact with eyes, rinse with plenty of water and seek medical advice accordingly.

If ingested, obtain medical attention immediately. Do not induce vomiting.

The information in this Technical Data Sheet is based on Colmef Monneli's experience. Colmef Monneli does not accept any liability arising from the use of its products as it has no direct or continuous control over where or how its products are applied. All Colmef Monneli's Data Sheets are updated on regular basis. It is the user's responsibility to obtain the latest version.

DUBAI ABU DHABI KSA ITALY
 P.O. Box 123808
 Dubai UAE

 P.O. Box 127326
 Abu Dhabi, UAE

 P.O. Box 335896
 Code: 11383 - Riyadh KSA

 Z.I. Ponte dÁssi
 06024 Gubbio (PG)

 T. +971 4 8803488
 F. +971 4 8803450

 T. +971 2 5511949
 F. +971 2 5511749

 T. +966 1 2654277
 F. +966 1 2654335

 T. +39 75 9221297
 F. +39 75 9221174

NEOCEM SCREED LC Technical Data Sheet Edition: January 2020 Revision: 02

colmef@colmef.ae

www.colmef-me.com